

#### Hefei TNJ Chemical Industry Co.,Ltd.

D1508 Xincheng Business Center, Qianshan Road, Hefei 230022 China

Tel: (0086) 551 65418678 Fax: (0086) 551 65418697 Email: info@tnjchem.com Site: www.tnjchem.com

# **Technical Data Sheet**

**Basic information** 

Chemical name 1,2-Octanediol Formula C8H18O2

Synonyms Octane-1,2-diol

CAS.No. 1117-86-8

EINECS No. 214-254-7

Molecular weight 146.23

Chemical structure

HO

**Physical properties** 

Appearance Colorless liquid or white crystalline

Density, g/cm3 0.914

Boiling point,  $^{\circ}$ C 131-132

Melting point,  $^{\circ}$ C 36-38

Flash point,  $^{\circ}$ C 138

Water solubility, g/L 3

#### **Specification**

Items Specification

Appearance Colorless ropy liquid

Assay, % ≥98.00

Moisture, % ≤0.50

### **Application**

- It is a good cold resistant plasticizer, suitable for artificial leather, film, sheet, wire and cable sheath, plastic plaster and so on.
- It can be used independently or in combination with other plasticizer nitrile rubber, styrene butadiene rubber, neoprene and other synthetic rubber plasticizer.
- Moisturizing agent with antibacterial activity in cosmetics.
- It is used for bathing and shampoo products, with thickening and stabilizing effect.

### **Package**

• 25kg per plastic drum, 12mt per 20'ft container or as per customer's requirements.









## Safety on transportation

It belongs to stable common material, always refer to MSDS.

### Storage and handling

Store in a cool, dry, well-ventilated area away from incompatible substances.

Please refer to the Materials Safety Data Sheet (MSDS) for the handling methods.

The information above is believed to be accurate and represents the best information currently available to us. However, In no event shall we be liable for any claims, losses, or damages of any third party resulting from its use.

**Issue Date**: 1st,12,2016